

ANTIPOR® 65 (ST)

Item No 2120

Stabiliser for concrete acc. to EN 934-2 with efflorescence decreasing effects

FIELDS OF APPLICATION

ANTIPOR® 65 (ST) is an admixture for producing semi-dry concrete and suitable for reducing efflorescence in manufactured concrete products like paving stones, slabs and tubes.

ANTIPOR® 65 (ST) allows an even and intense colouring of concrete and prevents it from sticking to the stamp.

DOSAGE

Recommended dosage range 0.2 – 0.4 mass-% of the cement content;
is equivalent to 2 – 4 ml per kg cement.

PROCESSING INDICATIONS

ANTIPOR® 65 (ST) should be added either to sand/gravel mix or to the premixed concrete batch.

This product is not classified as hazardous according to the EC directives, regulations on hazardous substances and forwarding instructions. The generally accepted precautions for handling chemicals must be followed. The corresponding Material Safety Data Sheet is available upon request.

PACKAGING

- 30 l can
- 200 l barrel
- 1000 l container

WORKING PRINCIPLE

ANTIPOR® 65 (ST) improves the cement dispersion within concrete which leads to a better workability and a facilitated compaction of concrete.

ANTIPOR® 65 (ST) can increase concrete's compressive- and bending pressure strength.

ANTIPOR® 65 (ST) generates a hydrophobic capillary system in concrete which minimises the transportation of solved calcium hydroxide to the surface. The occurrence of efflorescence is minimised thereby.

TECHNICAL DATA

Homogeneity	homogenous
Colour	yellowish
State	liquid
Density	1.04 ± 0.02 g/cm ³
pH-value	11 ± 1
Chloride content	< 0.10 mass-%
Alkali content (Na ₂ O equivalent)	< 4.0 mass-%
Workability	from +1 °C
Shelf life	approx. 1 year from date of production if stored properly
Storage conditions	Store in unopened, original sealed packaging between +5 °C and +25 °C. Protect from frost and insolation

REMARKS

This information describes the application- and processing possibilities of a product and its operation principles under regular conditions. Having no influence on the further application and processing, especially in conjunction with other construction materials, the given indication are neither a warranty in respect of the product's properties or its fitness for a particular purpose nor a full instruction of use.

This information, any other recommendation or verbal advice are not binding and do not infer to any liability or legal demand.

Due to continuous further development, the most recent Technical Data Sheet is valid and will be supplied on request. All orders are accepted subject to our current general terms and conditions.

Edition: 17 July 2019

SUITABILITY- AND PRE-TESTS ARE NECESSARY BEFORE APPLYING THE CONCRETE ADMIXTURE!