

PANTARHIT® FT750 (FM)

Item No 0858

High performance superplasticizer for concrete acc. to EN 934-2

Also suitable as concrete plasticizer PANTARHIT® FT750 (BV)

FIELDS OF APPLICATION

PANTARHIT® FT750 (FM) is a high performance superplasticizer for producing high consistency concrete at low water/cement ratios in precast concrete plants.

PANTARHIT® FT750 (FM) attains high early strength even in absence of heat treatment and under cold weather conditions. Thereby the stripping times are significantly reduced and the productivity can increase efficiently.

PANTARHIT® FT750 (FM) has excellent plasticizing effects which are able to enhance concrete's consistency by several classes e.g. from F1 up to F6 (is equivalent to S1 – S6). PANTARHIT® FT750 (FM) is particularly suitable for producing self compacting concrete (SCC).

PANTARHIT® FT750 (FM) may reduce the compaction energy applied to concrete. Concrete manufacturers, contractors and applicators may therefore achieve an economical and technical benefit.

DOSAGE

Recommended dosage range 0.2 – 2.65 mass-% of the cement content;
is equivalent to 2 – 25 ml per kg cement.

For F5 concrete | a = 620 mm

Having an initial consistency at the end of F1: approx. 8 ml per kg cement

For SCC and F6 concrete | a = 700 mm

Having an initial consistency at the end of F1: approx. 12 ml per kg cement

WORKING PRINCIPLE

PANTARHIT® FT750 (FM) improves the cement dispersion within the concrete significantly. This property allows the formation of a homogenous and low-viscosity cement paste which ensures an improved workability and facilitates the compaction of concrete.

PANTARHIT® FT750 (FM) ensures an extended workability time while the hydration development proceeds simultaneously. The special formulation meets the special requirements challenging the precast concrete industry.

TECHNICAL DATA

Homogeneity	homogenous
Colour	amber
State	liquid
Density	1.07 ± 0.02 g/cm ³
pH-value	6.5 ± 1
Chloride content	< 0.10 mass.-%
Alkali content (Na ₂ O-equivalent)	< 4.0 mass.-%
Workability	from +1 °C
Shelf life	approx. 1 year from date of production if stored properly
Storage conditions	Store in unopened, original sealed packaging between +5 °C and +25 °C. Protect from frost and insolation.

PROCESSING INDICATIONS

PANTARHIT® FT750 (FM) should be added to the ready-mixed concrete.

In forced action mixers the mixing time should be at least 60 seconds per cubic metre.

This product is not classified as hazardous according to the CLP regulations. See safety data sheet for further information.

PACKAGING

- 30 l can
- 200 l barrel
- 1000 l container
- loose by bulk supply

REMARKS

This information describes the application- and processing possibilities of a product and its operation principles under regular conditions. Having no influence on the further application and processing, especially in conjunction with other construction materials, the given indication are neither a warranty in respect of the product's properties or its fitness for a particular purpose nor a full instruction of use. This information, any other recommendation or verbal advice are not binding and do not infer to any liability or legal demand.

Due to continuous further development, the most recent Technical Data Sheet is valid and will be supplied on request. All orders are accepted subject to our current general terms and conditions.

Edition: 29 June 2020

SUITABILITY- AND PRE-TESTS ARE NECESSARY BEFORE APPLYING THE CONCRETE ADMIXTURE!