

# PANTARHIT<sup>®</sup> C120 (FM)

High performance superplasticizer acc. to EN 934-2 for concrete

Item No 0826

Also suitable as concrete plasticizer PANTARHIT<sup>®</sup> C120 (BV)

# **FIELDS OF APPLICATION**

PANTARHIT<sup>®</sup> C120 (FM) is a high performance superplasticizer suitable for enhancing the early strength development even at low ambient temperatures in precast and ready-mix concrete productions.

PANTARHIT<sup>®</sup> C120 (FM) is especially suitable for producing very free-flowing and self compacting concrete (F6 & SCC) (F6 is equivalent to S6).

PANTARHIT<sup>®</sup> C120 (FM) may reduce the compaction energy applied to concrete. Concrete manufacturers, contractors and applicators may therefore achieve an economical and technical benefit.

### DOSAGE

Recommended dosage range 0.2 - 2.1 mass-% of the cement content; is equivalent to 2 - 20 ml per kg cement.

**For F5 concrete | a = 620 mm** Having an initial consistency at the end of F1: approx. 15 ml per kg cement.

For SCC and F6 concrete | a = 700 mm Having an initial consistency at the end of F1: approx. 22 ml per kg cement.

## WORKING PRINCIPLE

PANTARHIT<sup>®</sup> C120 (FM) improves the cement dispersion within the concrete significantly. This property allows the formation of a homogenous and low-viscosity cement paste which ensures an improved workability and facilitates the compaction of concrete.

# **TECHNICAL DATA**

| Homogeneity                         | homogenous  |
|-------------------------------------|---|
| Colour                              | amber   |
| State                               | liquid  |
| Density                             | 1.05 ± 0.02 g/cm <sup>3</sup>   |
| pH-value                            | 6.0 ± 1   |
| Chloride content                    | < 0.10 mass-%   |
| Alkali content<br>(Na₂O-equivalent) | < 8.5 mass-%  |
| Workability                         | from + 1 °C   |
| Shelf life                          | approx. 1 year from<br>date of production if<br>stored properly   |
| Storage conditions                  | Store in unopened,<br>original sealed packag-<br>ing between +5 °C and<br>+25 °C. Protect from<br>frost and insolation. |



#### **PROCESSING INDICATIONS**

PANTARHIT<sup>®</sup> C120 (FM) should be added to the ready-mixed concrete.

In forced action mixers the mixing time should be at least 60 seconds per cubic metre.

On site, concrete's mixing time in truck mixers should be 60 seconds per cubic metre, but not less then five minutes.

This product is not classified as hazardous according to the EC directives, regulations on hazardous substances and forwarding instructions The generally accepted precautions for handling chemicals must be followed. The corresponding Material Safety Data Sheet is available upon request.

# PACKAGING

#### - 301 can

- 200 l barrel
- 1000 l container
- loose by bulk supply

#### REMARKS

This information describes the application- and processing possibilities of a product and its operation principles under regular conditions. Having no influence on the further application and processing, especially in conjunction with other construction materials, the given indication are neither a warranty in respect of the product's properties or its fitness for a particular purpose nor a full instruction of use. This information, any other recommendation or verbal advice are not binding and do not infer to any liability or legal demand.

Due to continuous further development, the most recent Technical Data Sheet is valid and will be supplied on request. All orders are accepted subject to our current general terms and conditions.

Edition: 18 March 2020

SUITABILITY- AND PRE-TESTS ARE NECESSARY BEFORE APPLYING THE CONCRETE ADMIXTURE!