

# PANTARHIT® RC550 (FM) Superplasticizer for concrete acc. to EN 934-2

Item No 0825

Also suitable as concrete plasticizer PANTARHIT<sup>®</sup> RC550 (BV)

## **FIELDS OF APPLICATION**

PANTARHIT<sup>®</sup> RC550 (FM) is a high performance superplasticizer for ready-mix concrete with prolonged workability retention in different consistency classes and allows high early and final strength developments in concrete.

PANTARHIT<sup>®</sup> RC550 (FM) has excellent plasticizing effects which are able to enhance concrete's consistency by several consistency classes e.g. from F1 up to F6 (is equivalent to S1 - S6).

#### DOSAGE

Recommended dosage range 0.2 - 2.15 mass-% of the cement content; is equivalent to 2 - 20 ml per kg cement.

For F5 concrete | a = 620 mm Having an initial consistency at the end of F1: approx. 10 ml per kg cement

High doses might slightly impair the early strength development.

## WORKING PRINCIPLE

PANTARHIT<sup>®</sup> RC550 (FM) improves the cement dispersion within the concrete significantly. This property allows the formation of a homogenous and low-viscosity cement lime which ensures an improved workability and facilitates the compaction of concrete.

PANTARHIT<sup>®</sup> RC550 (FM) advances the pumping and placing of concrete and improves its processing and compaction significantly.

### **TECHNICAL DATA**

Homogeneity	homogenous
Colour	brown
Chemical base	modified polycarbox- ylates, lignosulfonates
State	liquid
Density	1.08 ± 0.03 g/cm <sup>3</sup>
pH-value	6 ± 1
Chloride content	< 0.10 mass-%
Alkali content (Na₂O equivalent)	< 4.0 mass-%
Workability	from +1 °C
Shelf life	approx. 1 year from date of production if stored properly
Storage conditions	Store in unopened, original sealed packag- ing between +5 °C and +25 °C. Protect from frost and insolation.



#### **PROCESSING INDICATIONS**

PANTARHIT<sup>®</sup> RC550 (FM) should be added to the ready-mixed concrete.

In forced action mixers the mixing time should be at least 60 seconds per cubic metre.

On site, concrete's mixing time in truck mixers should be 60 seconds per cubic metre, but not less then five minutes.

This product is not classified as hazardous according to the EC directives, regulations on hazardous substances and forwarding instructions. The generally accepted precautions for handling chemicals must be followed. The corresponding Material Safety Data Sheet is available upon request.

## REMARKS

This information describes the application- and processing possibilities of a product and its operation principles under regular conditions. Having no influence on the further application and processing, especially in conjunction with other construction materials, the given indication are neither a warranty in respect of the product's properties or its fitness for a particular purpose nor a full instruction of use. This information, any other recommendation or verbal advice are not binding and do not infer to any liability or legal demand.

Due to continuous further development, the most recent Technical Data Sheet is valid and will be supplied on request. All orders are accepted subject to our current general terms and conditions.

Edition: 19 March 2020

#### PACKAGING

- 301 can
- 200 l barrel
- 1000 l container
- loose by bulk supply

SUITABILITY- AND PRE-TESTS ARE NECESSARY BEFORE APPLYING THE CONCRETE ADMIXTURE!