

## PANTARHIT® RC172 (FM)

Item No 0819

**High performance superplasticizer acc. to EN 934-2 for ready-mix concrete**

Also suitable as concrete plasticizer PANTARHIT® RC172 (BV)

### FIELDS OF APPLICATION

PANTARHIT® RC172 (FM) is a high performance superplasticizer for ready-mix concrete with prolonged workability retention in the consistency classes F3 – F6 (is equivalent to S3 – S6) and allows high early and final strength developments in concrete.

PANTARHIT® RC172 (FM) has excellent plasticizing effects which are able to transform stiff concrete (F1) up to flow concrete (F6)(is equivalent to S1 – S6). The high performance superplasticizer is especially suitable for producing self and easily compacting concrete.

PANTARHIT® RC172 (FM) may reduce the compaction energy applied to concrete. Concrete manufacturers, contractors and applicators may therefore achieve an economical and technical benefit.

### DOSAGE

Recommended dosage range 0.2 – 2.2 mass-% of the cement content; is equivalent to 2 – 21 ml per kg cement.

### WORKING PRINCIPLE

PANTARHIT® RC172 (FM) improves the cement dispersion within the concrete significantly. This property allows the formation of a homogenous and low-viscosity cement paste which ensures an improved workability and facilitates the compaction of concrete.

Its special built extends the processing time purposefully and meets the special requirements challenging the ready-mix concrete industry.

### TECHNICAL DATA

Homogeneity	homogenous
Colour	amber
State	liquid
Density	1.06 ± 0.02 g/cm <sup>3</sup>
pH-value	6 ± 1
Chloride content	< 0.10 mass-%
Alkali content (Na <sub>2</sub> O equivalent)	< 8.5 mass-%
Workability	from +1 °C
Shelf life	approx. 1 year from date of production if stored properly
Storage conditions	Store in unopened, original sealed packaging between +5 °C and +25 °C. Protect from frost and insolation.

## PROCESSING INDICATIONS

---

PANTARHIT® RC172 (FM) should be added to the ready-mixed concrete.

In forced action mixers the mixing time should be at least 60 seconds per cubic metre.

On site, concrete's mixing time in truck mixers should be 60 seconds per cubic metre, but not less than five minutes.

This product is not classified as hazardous according to the EC directives, regulations on hazardous substances and forwarding instructions. The generally accepted precautions for handling chemicals must be followed. The corresponding Material Safety Data Sheet is available upon request.

## PACKAGING

---

- 30 l can
- 200 l barrel
- 1000 l container
- loose by bulk supply

## REMARKS

---

This information describes the application- and processing possibilities of a product and its operation principles under regular conditions. Having no influence on the further application and processing, especially in conjunction with other construction materials, the given indication are neither a warranty in respect of the product's properties or its fitness for a particular purpose nor a full instruction of use. This information, any other recommendation or verbal advice are not binding and do not infer to any liability or legal demand.

Due to continuous further development, the most recent Technical Data Sheet is valid and will be supplied on request. All orders are accepted subject to our current general terms and conditions.

Edition: 19 March 2020

**SUITABILITY- AND PRE-TESTS ARE NECESSARY BEFORE APPLYING THE CONCRETE ADMIXTURE!**