

## ANTIPOR® 54 (ST)

Stabiliser for concrete acc. to EN 934-2 with plasticizing effects

Item No 2030

### FIELDS OF APPLICATION

ANTIPOR® 54 (ST) is an admixture for producing semi-dry concrete and suitable for manufactured concrete products like paving stones, paving flags and tubes.

### DOSAGE

Recommended dosage range 0.2 – 0.6 mass-% of the cement content;  
is equivalent to 2 – 5 ml per kg cement.

### PROCESSING INDICATIONS

ANTIPOR® 54 (ST) should be added either to the sand/gravel mix or to the premixed concrete batch.

This product is not classified as hazardous according to the CLP regulations. See safety data sheet for further information.

### PACKAGING

- 30 l can
- 200 l barrel
- 1000 l container

### WORKING PRINCIPLE

ANTIPOR® 54 (ST) achieves a denser concrete texture with closed surfaces. The early and final strength are increased.

### TECHNICAL DATA

Homogeneity	homogenous
Colour	dark brown
State	liquid
Density	1.16 ± 0.02 g/cm <sup>3</sup>
pH-value	4.5 ± 1.0
Chloride content	< 0.10 mass-%
Alkali content (Na <sub>2</sub> O equivalent)	< 4.0 mass-%
Workability	from + 1°C
Shelf life	approx. 1 year from date of production if stored properly
Storage conditions	Store in unopened, original sealed packaging between +5 °C and +25 °C. Protect from frost and insolation.

## REMARKS

---

This information describes the application- and processing possibilities of a product and its operation principles under regular conditions. Having no influence on the further application and processing, especially in conjunction with other construction materials, the given indication is neither a warranty in respect of the product's properties or its fitness for a particular purpose nor a full instruction of use.

This information, any other recommendation or verbal advice are not binding and do not infer to any liability or legal demand.

Due to continuous further development, the most recent Technical Data Sheet is valid and will be supplied on request. All orders are accepted subject to our current general terms and conditions.

Edition: 26 April 2022

**SUITABILITY- AND PRE-TESTS ARE NECESSARY BEFORE APPLYING THE CONCRETE ADMIXTURE!**