

## CLEANER BSR

**Special cleaning agent for removing efflorescence**

Item No 1130

### FIELDS OF APPLICATION

CLEANER BSR is a highly efficient cleaning agent for removing efflorescence and cement residues from all natural and artificial stone surfaces such as concrete blocks, precast elements, facades, and slabs.

### APPLICATION QUANTITY

Depending on the surface structure, its absorbency, and its contamination level, approx. 40 – 100 g/m<sup>2</sup> are necessary.

### PROCESSING INDICATIONS

CLEANER BSR is either applied undiluted or diluted to the pre-moistened surface.

If a diluted mixture is requested dilute CLEANER BSR with clean water in the ratio 1:3 to 1:5, apply and allow to work.

After 2 to 5 minutes remove efflorescence or cement residues with a brush, scrubbing brush or cleaning automat.

After the mixture is absorbed, the surface should be rinsed with water. Repeat treatment if necessary.

Corrosive materials should be cleaned with water immediately.

This product is classified as hazardous according to the CLP regulations. See safety data sheet for further information.

### PACKAGING

- 20 l can

### WORKING PRINCIPLE

CLEANER BSR reacts chemically with the existing efflorescence or cement residues. In so doing the solvent-free cleansing agent forms an effective substance that removes them.

### TECHNICAL DATA

Homogeneity	homogenous
Colour	colourless
State	liquid
Density	1.10 ± 0.03 g/cm <sup>3</sup>
Workability	from +5 °C to 20 °C
Shelf life	approx. 1 year from date of production if stored properly
Storage conditions	Store in unopened, original sealed packaging between +5 °C and +25 °C. Protect from frost and insolation.

## REMARKS

---

This information describes the application- and processing possibilities of a product and its operation principles under regular conditions. Having no influence on the further application and processing, especially in conjunction with other construction materials, the given indication is neither a warranty in respect of the product's properties or its fitness for a particular purpose nor a full instruction of use.

This information, any other recommendation or verbal advice are not binding and do not infer to any liability or legal demand.

Due to continuous further development, the most recent Technical Data Sheet is valid and will be supplied on request. All orders are accepted subject to our current general terms and conditions.

Edition: 30 March 2023

**SUITABILITY- AND PRE-TESTS ARE NECESSARY BEFORE APPLYING THE CONCRETE ADMIXTURE!**